

(12) UK Patent Application (19) GB (11) 2 070 627 A

(21) Application No 8100784
(22) Date of filing 30 May 1980
(30) Priority data

(31) 2783403
(32) 19 Jul 1979
(33) Soviet Union (SU)
(43) Date of issue
9 Sep 1981

(51) INT CL³
(As given by ISA)
B22C 1/18 C04B 35/04
(52) Domestic classification
C3N 25 25D1C 25F1 25F2
25F3 25F4 25FX 25G6

(56) Documents cited by ISA
SU, A, 339090
JP, A, 52-23882

(58) Field of search by ISA
INT CL B22c 1/00-1/20;
C04b 35/04
INT CL² B22c 1/00-1/20;
C04b 35/04
German 80b 801-802;
80b 8091
US 164-136; 164-41
GB 83(1)F; B3F
FR Group 7, Class 2
AT 49f; 80C
AU 70.2
CA 22; 261

(71) Applicants
Nauchno-
Proizvodstvennoe
Obedinenie Po
Tekhnologii
Mashinostroeniya
(Tsnitmash), Sharikopod-
shipnikovskaya, Ulitsa 4,
Moscow, Soviet Union

(72) Inventors
Yuly Moiseevich
Yunovich,
Viktor Naumovich
Pertsovsky,
Igor Petrovich Renzhin,
Sergei Semenovich
Zhukovsky,
Vyacheslav Sergeevich
Kolesnikov,
Olga Evgenevna Nevskaya

(74) Agents
Marks & Clerk, 57—60
Lincoln's Inn Fields,
London WC2A

(54) Self-hardening compound for
making casting moulds and cores

(57) A self-hardening compound for
making casting moulds and cores
containing a refractory filler,
orthophosphoric acid, a magnesia-
spinellid-type compound roasted at a
temperature of 1600 to 1900°C
during 40 to 1600 hours, and water at

the following ratio of the said
components in parts by weight:

orthophosphoric acid 2—10

the said magnesia-spinellid-
type compound 2—20

water 0.5—6.0

refractory filler balance

GB 2 070 627 A